



# PRODUCT INFORMATION

MARTRON INC.<sup>®</sup> P O BOX 309, MONROE, NC 28111 PH: (704) 289-1934 FAX: (704) 283-7400

DATE: NOVEMBER 1, 2011

EMERGENCY - MARTRON 704-289-1934  
CHEMTREC 800-424-9300

REF. # MFC-005003

## MARTRON GOLD S DYE

### 1. Description

**Martron Gold S Dye** is a single component, water soluble dye, used to color anodized aluminum gold, similar to 14 karat gold.

RoHS compliant

### 2. Application Instructions

Concentration:	1-2 g/l
pH:	6.0 ±0.5
Buffering:	Not required
Temperature:	140°F ± 5°F/60°C
Oxide film thickness:	0.20-0.40 mils.
Dye time:	Depending on the shade desired, dye times could range from 2-5 minutes, but can only be determined by sampling in plant production.
Preferred sealing:	Specialty Sealant MTL Specialty Sealant

### 3. Conditions for Using Martron Gold S Dye

Tank:	Stainless steel or other acid resistant materials such as neoprene, polyethylene and polypropylene that can withstand a constant operating temperature of 140°F.
Water quality:	Deionized
pH adjustments:	Raise with sodium hydroxide. Lower with acetic acid. The pH should be checked once per shift with a calibrated meter and maintained within recommended range.
Bath agitation:	Moderate agitation must be used for high uniformity of color.
Rinsing:	It is important to remove all acid residues clinging to the work and acid retention in the oxide pore itself. Rinse work load thoroughly after anodizing.

A minimum of two rinses is recommended, with the second rinse at over-flow.

To increase rinsing effectiveness, add vigorous air agitation in all rinse tanks. This also improves your rinsing of surfaces on complicated shaped parts.

#### 4. Light Fastness

Rating: 5 (1=poor, 8=excellent)

This color is not recommended for outdoor applications or other situations where it is subjected to intense UV radiation.

#### 5. Storage

Shelf life is virtually unlimited.

Store in original container in a cool dry location.

Close package tightly after removal of dye.

In humid environments, dye powder may clump-up.

#### 6. Preparation of A New Dye Bath

1. A cleaned tank is filled with deionized water to about 75% of final volume and raised to dyeing temperature.
2. The required amount of dye is weighed out and dissolved in hot deionized water (160°-180°F) in a separate container until a slurry is formed. This is your stock solution.
3. With agitation turned on in tank, pour stock solution into tank.
4. Top off the tank to final working solution volume with hotter deionized water and agitate for 15 minutes.
5. Using a calibrated pH meter, check the pH and adjust if necessary.
6. The dye bath is brought to dyeing temperature, 140°F ±5°F.

#### 7. Conversion Factor

Converting grams per liter (g/l) to ounces per gallon (oz/gal)

$$\text{g/l} \times 0.134 = \text{oz/gal}$$

#### 8. Product Safety

We recommend that the company/operator read and review the Safety Data Sheet (SDS) for the appropriate health and safety warnings before use.

**Martron Inc.** recommendations, notices or instructions as to handling, use, storage of any product, including its use alone or in combination with other products, or as to any apparatus or process for the use of any product, are based upon information believed to be reliable, but **Martron Inc.** shall have no liability with respect to any recommendations or instructions. **Martron Inc.** sole and exclusive warranty is that its products comply with **Martron Inc.** published chemical and physical specifications. **Martron Inc.** makes no other warranties, other express or implied with respect to its recommendations, instructions, products, apparatus, and process or otherwise and specifically disclaims any implied warranties of merchantability, suitability, fitness for a particular or otherwise.